

## TRU-MOTION SS

### IAAF CERTIFIED IMPERMEABLE TRACK



**Tru-Motion SS is an IAAF Certified Track construction meeting the standards for Structural Spray and Sealed systems. It is composed of three layers:**

#### Base Mat

Tru-Motion H3313 and 1-4 mm SBR crumb

Tru-Motion H3313 is a 100% solids, TDI/MDI combination, moisture cure polyurethane binder for use in the construction of bonded rubber granule running tracks and similar athletic surfaces. Tru-Motion H3313 is carefully controlled for TDI content during manufacturing to minimize regulatory and construction site safety hazards associated with the use of TDI containing systems. It is designed to have optimized handling characteristics for track installation combined with high physical properties.

TRU-MOTION H3313 CONTAINS TDI AND IS FOR INDUSTRIAL OR COMMERCIAL USE ONLY. NOT FOR USE BY CONSUMERS OR SALE OR RESALE TO CONSUMERS.

#### Seal Coat

Tru-Motion S9326/H9417 is a thixotropic two-component polyurethane sealer. It is designed to seal surface porosity of rubber mats, and even up the seams, prior to the application of the polyurethane wear coatings. It is TDI, mercury, and heavy metal free, eliminating the regulatory problems and construction site hazards associated with products containing these materials.

#### Structural Spray

Tru-Motion S9006/H3020 Structural Spray Coating System is a two-component, high solids, mercury, heavy metal, and TDI free structural spray system for running tracks and similar athletic surfacing applications. In order to simplify the inventory requirements of installers, Tru-Motion S9006 pigmented base component utilizes Tru-Motion H3020 TDI free polyurethane track binder as the reactive urethane component of the structural spray coating system.

#### SYSTEM APPLICATION DATA

	Products	Typical Consumption	Application
Base Mat	H3313	3.75 lb./yd <sup>2</sup> (2.03 kg/m <sup>2</sup> )	Paver
	Recycled Rubber Granules, 1-4mm	15.0 lb./yd <sup>2</sup> (8.13 kg/m <sup>2</sup> )	
Pore Sealer	S9326	1.60 lb./yd <sup>2</sup> (0.88 kg/m <sup>2</sup> )	Squeegee (or paver)
	H9417	1.60 lb./yd <sup>2</sup> (0.88 kg/m <sup>2</sup> )	
Coating	H3020	1.54 lb./yd <sup>2</sup> (1.04 kg/m <sup>2</sup> )	Spray
	S9006	0.38 lb./yd <sup>2</sup> (0.21 kg/m <sup>2</sup> )	
	EPDM Granules, 0.5-1.5	1.28 lb./yd <sup>2</sup> (0.69 kg/m <sup>2</sup> )	

DISCLAIMER: THE DATA PRESENTED HEREIN IS NOT INTENDED FOR USE BY NON-PROFESSIONAL APPLICATORS, OR THOSE PERSONS WHO DO NOT PURCHASE OR UTILIZE THIS PRODUCT IN THE NORMAL COURSE OF THEIR BUSINESS. THE POTENTIAL USER MUST PERFORM ANY PERTINENT TEST IN ORDER TO DETERMINE THE PRODUCT'S PERFORMANCE AND SUITABILITY IN THE INTENDED APPLICATION: FINAL DETERMINATION OF QUALIFICATION FOR SAID PRODUCT IN ANY PARTICULAR APPLICATION IS THE RESPONSIBILITY OF THE BUYER/USER.

CALL CARLISLE POLYURETHANE SYSTEMS FOR TECHNICAL QUESTIONS.  
(888) 899-9665.

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. CARLISLE POLYURETHANE SYSTEMS WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES. CARLISLE POLYURETHANE SYSTEMS EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE CARLISLE POLYURETHANE SYSTEMS OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.

